


Received: 01/15/2010	Completed: 01/21/2010	Letter: S	rb	P.O.#:	Test Report #: 2-81817-0- RV
----------------------	-----------------------	-----------	----	--------	------------------------------

Client's Identification Style: KML 22 Seamless Mesh. Date of Mfg: 27/8/09. Composition: KML22 FR. Weight: 2kg/m². Density: 142.3kgm³.
Thickness: 14mm. (see continuation)

Tested For: Kayne Horsham Kaynemaile Ltd. Unit 2, 85 Hutt Road, Thorndon Wellington 6035 NEW ZEALAND	Key Test: NFPA 701-2004 TM#2 Flat RVNC Tel: 011 64 4 473 4989 Ext: Fax: 011 64 4 471 4640
----------------------------------------------------------------------------------------------------------------------	------------------------------------------------------------------------------------------------------------

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2004 Edition Test Method #2 Flat Sheet Specimens.



Robert I. Brown

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. / ec

JAN 28 2010
RV. 01.27.10 /mg

PRECONDITIONING: 1 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:
None.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)

Received:01/15/2010 Completed:01/21/2010 Letter: S rb P.O.#: Test Report #: 2-81817-0- RV

Client's Identification Style: KML 22 Seamless Mesh. Date of Mfg: 27/8/09. Composition: KML22 FR. Weight: 2kg/m². Density: 142.3kgm³. Thickness: 14mm. (see continuation)

Tested For: **Kayne Horsham** Key Test: NFPA 701-2004 TM#2 Flat RVNC
Kaynemaile Ltd.
Unit 2, 85 Hutt Road, Thorndon Tel: 011 64 4 473 4989 Ext:
Wellington 6035 NEW ZEALAND Fax: 011 64 4 471 4640

CLIENT'S IDENTIFICATION (continuation):

Architectural Design and Detailing Non Structural.

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2004 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	216
2	0	0	226
3	0	0	150
4	0	0	220
5	0	0	290
6	0	0	240
7	0	0	230
8	0	0	216
9	0	0	230
10	0	0	216

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails; Requires testing of 5 additional specimens